

Ethylux® is a Registered Trademark of Westlake Plastics Co.

Ethylux is made from low density polyethylene resin. This material is a cost e ective option for a variety of end uses including mild chemical and wear applications.







The following physical property information is based on typical values of the base low density polyethylene resin

Property	Units	Test Standard	Result
Mechanical			
Tensile Elongation @break	%	ASTM D638	650
Tensile Strength @break	psi	ASTM D638	1,800
Hardness	D Scale	ASTM D2240	D42
Thermal			
Flammability Rating	_	UL94	НВ
Heat Deflection Temperature @66 psi	°F	ASTM D648	120
Low Temperature Brittleness	°F	ASTM D746	-103
Vicat Softening Temperature	°F	ASTM D1525	185
Electrical			
Dielectric Constant @60Hz	_	ASTM D1502	2.63
Dissipation Factor @60Hz	_	ASTM D150	0.006
Dielectric Strength @.125"	V/mil	ASTM D149	488
Other			
Specific Gravity	_	ASTM D792	0.919
Water Absorption @24 hours	%	ASTM D570	0.04

Applications Include:

- -Low load tank linings
- Vacuum formed end caps and tops
- Orthopaedic appliances
- Electical insulators
- Beverage, drug and chemical containers
- Bags and liners

Manufacturing Capabilities:



Colors:

Natural

In addition to our standard capabilities, Westlake also has the ability to process custom resins in various sizes and colors with some exceptions.

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential class) shall be available to the buyer.



Phone : 1.610.459.1000 Phone : 1.800.000.1700 Fax : 610.459.1084

490 West Lenni road Lenni, PA 19052 U.S.A

Email: info@westlakeplastics.com



