

# ZELUX® CN-P

## ElectroStatic Discharge

Zelux® is a Registered Trademark of Westlake Plastics Co.



Electrical Properties	Test Method	Result	
		Metric	English
Surface Resistivity dry	ASTM D257	10 <sup>3</sup> - 10 <sup>6</sup> ohm/sq	10 <sup>3</sup> - 10 <sup>6</sup> ohm/sq
Volume Resistivity dry	ASTM D257	10 <sup>3</sup> - 10 <sup>6</sup> ohm-cm	3937 - 39370080.00 ohm-in
Static decay	Mil-B-81705-B	< 0.1 seconds	< 0.1 seconds
Mechanical Properties	Test Method	Result	
		Metric	English
Tensile Strength at yield	ASTM D638	65 MPa	9.4 kpsi
Tensile Elongation at break	ASTM D638	5 %	5 %
Flexural Strength	ASTM D790	107 MPa	15.5 kpsi
Flexural Modulus	ASTM D790	3172 MPa	460 kpsi
Izod Impact Strength Notched	ASTM D256	0.75 J/cm	1.4 ft-lb/in
Izod Impact Strength Un-notched	ASTM D256	5.3 J/cm	10 ft-lb/in
Hardness-Shore D	ASTM D2240	62	62
Other Properties	Test Method	Result	
		Metric	English
Specific Gravity	ASTM D792	1.32	1.32
Water Absorption at 24 hours	ASTM D570	0.16 %	0.16 %
Thermal Properties	Test Method	Result	
		Metric	English
Heat Deflection Temp. at 264 psi	ASTM D648	132 °C	270 °F
Flam. Rating-UL94	-	V-0 at 0.028	V-0 at 0.028
Coefficient of Thermal Expansion	ASTM D696	m/m/°C	in/in/°F
Thermal conductivity	-	watt-meter/K	BTU-in/hr-ft <sup>2</sup> -°F

### Applications Include:

- Semiconductor/electronic components
- Cassette housings
- Telecommunications hardware
- Explosives handling equipment

### Manufacturing Capabilities:



### Colors:

**Black**

In addition to our standard capabilities, Westlake also has the ability to process custom resins in various sizes and colors with some exceptions.

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.



Phone : 1.610.459.1000  
Phone : 1.800.000.1700  
Fax : 610.459.1084

490 West Lenni road  
Lenni, PA 19052  
U.S.A

Email : info@westlakeplastics.com

**CLICK TO OUR WEBSITE**



EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.